



INNOVATION

OIL AND LACQUER

Solid'Oil™ + Intensiv™ CONCEPT

THE DECOR TOUCH OF AN OIL AND THE PERFORMANCE OF A LACQUER

▶ A WINNING CONCEPT

- 3 coats for a finished stain and lacquered floor
- Easy colour oiling
- The guarantee of a successful site

▶ NEW AMBIENCES

- A wide range of 41 colours (30 of which are new) to satisfy all your decorating needs
- New decorative options with 6 lacquered finishes: gloss, satin, matt, ultra-matt and Invisible effect and Bare timber effects to enhance light shades

▶ INIMITABLE FINAL RESULT

Depth of colour of the oil and ease of maintenance of the lacquered floor



A single-coat high solid hard wax oil

2-component water-based polyurethane lacquer



An infinite choice of colours for an incomparable finish

Resistant to heavy use and preserves the look of the coloured oil

Blanchon

PREPARATION AND USAGE



1 ► SANDING INSTRUCTIONS

- Bring back to bare wood through classic sanding
- Final sanding by using 80-grit (max) sandpaper
 - Open the wood pores
 - Optimise the penetration of Solid'Oil™ and the wood colouring process



2 ► DECORATING WITH SOLID'OIL™

- Solid'Oil™* (coloured versions) application, catalysed by 20% with Oil Hardener, with a roll or a double-blade spatula, followed by 10 minutes of polishing with a beige pad (quantity used for the 1st coat: 35m²/L for oak)
- If a 2nd coat is needed (for a more intense colour), it is applied using the same process

* Solid'Oil™ + Intensiv™ is not compatible with the **Natural 100%** shade (alone or combined with other shades of Solid'Oil™)

3 ► LACQUERING WITH INTENSIV™

- Wait at least 24 hours (and maximum 36 hours)
- To check if the oil is completely dry: quick polish with a new beige pad (no traces on the pad = the floor can be coated with Intensiv™)
- Application of 2 coats:
 - with a roller, and a spalter for the edges
 - 3-hour interval



OUR FAVORITES



Solid'Oil™
White grey
+ Intensiv™
Invisible
Effect



Solid'Oil™
Snow
+
Intensiv™ Bare
timber



Solid'Oil™
Old Castle
+
Intensiv™
Ultra-matt

Head office, Technical and Sales departments
BLANCHON
50 8^{ème} Rue - CS 60019
69800 SAINT-PRIEST CEDEX - FRANCE
Export Direct Lines : +33 472 89 06 09



www.blanchon.co.uk

Blanchon