

Multi-finishes  
Heavy traffic

Odourless

High chemical  
resistance

Quick drying

Preserves the natural  
colour of the wood

All premises subject to  
heavy traffic: schools,  
shops, public buildings,  
offices, etc.

It can be used on its  
own, or on PRIM'SEALER,  
PRIM'GOLD or  
S.O. PRIMER.

Fireproofed  $C_{fi}S1^{**}$

EC1R Certification

# Intensiv™



## PRODUCT DESCRIPTION

- BLANCHON INTENSIV™ is a 2-component, water-based polyurethane wood floor lacquer. Its technical performance and formulation meet the most stringent ecological criteria. It is also certified by the German label GEV-EMICODE® EC1R for the most ecological approach to indoor work.
- INTENSIV™ is odourless, and Aqua Pro is a true, water-soluble polyurethane hardener.
- INTENSIV™ is based on complex carbon resins, selected for their unequalled resistance to wear, abrasion and scratching, and which do not react to potentially corrosive substances: cleaning agents, disinfectant, alcohol, wine, tea, ink, sauces, etc.
- Thanks to exceptional performance and fast drying time, its components make INTENSIV™ ideal for all floor sealing jobs, especially in high-traffic areas: shops, offices, hotels, conference rooms, schools, corridors and entrance halls.
- INTENSIV™ can be applied on all types of commonly used wood (please contact us for information on rare woods, also beech and walnut). Its colourless appearance protects and enhances the grain and tone of the wood.
- 5 finishes for all wood species: gloss, satin, matt, ultra-matt and invisible effect. The 6<sup>th</sup> finish: bare timber was specially designed to maintain the original appearance of light coloured types of wood and will only be applied to this type of wood species.
- Can be used on interior concrete.

\*\*Fire classification C<sub>f</sub>S1 obtained on an 8mm oak or beech floor glued to the supporting surface.

## SURFACE PREPARATION

- Sand old or new wood flooring to obtain a smooth, even surface: first sand to bare wood with 24 or 36 grit, then with 50 or 60 grit and finish with 100 or 120 (see § APPENDIX).
- Remove all traces of dust.
- The wood floor must be perfectly clean and dry. As a general rule, moisture content should be below 10%. Consult the DTU in force (do not use detergents or whiteners).
- For glued down wood flooring, use BLANCHON PRO FILLER (water-based filler), or BLANCHON RESIN FILLER for filling and colour-matching (please consult Technical Data Sheets for these products).

### Insecticide treatment

- If necessary, use a suitable treatment product.

### Wood staining

- Floors sanded back to bare wood can be stained with BLANCHON AQUATEINTE™ 2K. After the stain has dried, apply 3 coats of INTENSIV™ directly on top or alternatively, apply BLANCHON PRIM'SEALER or PRIM'GOLD and then 2 coats of INTENSIV™.
- Sanded floors (to bare wood) can be stained using BLANCHON WATERBORNE DYE or BLANCHON WOOD AGEING AGENT (positive shades). When using these products, once the stain has dried, apply 1 coat of BLANCHON S.O. PRIMER to fix the stain (do not use PRIM'SEALER or PRIM'GOLD in this particular case). Then apply INTENSIV™.
- In all cases, never sand the stain itself, but only the first coat of finishing product, in order to maintain the quality of the stain.
- It is also recommended to cut back with fine sandpaper prior to applying the final coat.
- Do not use woodstain.

### Use of primers

- The following BLANCHON primers may be used as a base coat: PRIM'SEALER, PRIM'GOLD or S.O. PRIMER (please consult the relevant Technical Data Sheets).
- The use of PRIM'SEALER or PRIM'GOLD allows fast completion with an easy and odourless application. The colour obtained with PRIM'SEALER gives the wood a colouration identical to that achieved with INTENSIV™ used on its own. PRIM'GOLD gives the wood a deep and warm colouration - especially when applied to high-tannin woods such as oak or chestnut - close to the one achieved using a coat of S.O. PRIMER.
- Using S.O. PRIMER allows fast sealing and gives the wood a lovely natural warmth enhancing the initial tone. It is essential to use S.O. PRIMER to fix BLANCHON WATERBORNE DYE and BLANCHON WOOD AGEING AGENT before sealing with INTENSIV™ (see § WOOD STAINING).

## DIRECTIONS FOR USE

### Preparation

- Shake Component A vigorously.
- The INTENSIV™ Lacquer (Comp. A) and AQUA PRO Hardener (Comp. B) should be mixed together immediately before use. Always use the following measures: B: 1 part to 9 parts of Comp. A [by volume].
- Mix immediately and thoroughly for 2 to 3 minutes. The mixture should be used within 90 minutes.
- No dilution required.
- NB: INTENSIV™ comes in special packaging (separable container) which can be used directly for mixing and application. Place the plastic bag in one half of the pre-cut container to form a bowl for making up the mixture.

### Application

- Do not lacquer the wood floor if the temperature is lower than 12°C or if the relative humidity is higher than 85% (in accordance with the DTU in force); do not use on wood with a moisture content above 10%. Use only in well-ventilated areas.
- The product is applied with a roller (short-haired) in 3 regular and generous coats, or with a spatula for multiple coats. Alternatively, you can apply 2 coats on top of a primer (see § SURFACE PREPARATION).
- If applying with a spatula (multiple coats), you should sand and remove dust before applying the final coat of INTENSIV™ with a roller. Do not apply INTENSIV™ with a spatula on beech, maple or cherry.
- Once the first coat has dried, a light sanding is recommended with a buffing machine (fine sanding disc) before removing all traces of dust. Sanding is essential if more than 24 hours elapse between coats.
- When applying the bare timber finishing, you are advised to sand between each coat using worn 150 or 120 grit paper.

### Surface preparation and application on concrete

- Very easy to use, INTENSIV™ provides long-term protection against stains, dust and humidity. The treated surfaces are discreetly enhanced (wax finish), and are easy to maintain, even in high-traffic areas, concrete floors, worktops, etc. that are clean and bare (without other coatings such as wax, oil, varnish, etc.).
- Not suitable for water containers: sinks, showers, bowls, bathtubs, etc.

# Blanchon

# Intensiv™

- Check the porosity of the material, necessary for good adhesion: one spoonful of water poured onto clean concrete should penetrate in 1 minute. Repeat the test in different areas. Clean thoroughly with a vacuum cleaner, then with a damp mop. Allow to dry.
- Do not apply if the temperature of the surface is below 12°C or if the moisture content is greater than 5% (use of a moisture meter is recommended). The relative humidity of the room must not exceed 85%. Use only in well ventilated areas.
- Apply 2 coats in the direction of the light using a short-haired roller (use a brush or graining brush from the edges of the room). The coat should be thin, using approximately 1 litre per coat for 12 to 15 m<sup>2</sup>. Apply evenly, avoiding areas of over- or under-application.

## Cleaning of tools

- Clean tools with water immediately after use. Do not reuse the containers.
- Protecting the environment:
  - Carefully remove excess moisture from the equipment after application; dry thoroughly.
  - Rinse using very little water in a container; allow the water to evaporate.
  - The dry residue may then be disposed of normally in a bin.
  - Seal the container properly after use.
  - Do not discharge the residue into drains.
  - Dispose of empty containers at a waste recycling centre.

## DRYING TIMES

- Dust-free drying: 45 minutes under normal conditions.
- Before sanding/recoating: 4 hours in normal conditions.
- Do not wait more than 24 hours between coats.
- Curing time: 8 to 10 days.
- Light traffic: approximately 24 hours under normal conditions.
- Occupation of the premises: during the first 10 days take some precautions: do not cover (protective sheets), do not place carpets on the lacquered wood floor during this period. Do not move heavy furniture. Remove dust with a vacuum cleaner or broom (do not use impregnated textiles).
- Next: place suitable protection (felt) under the feet of tables and chairs. If necessary, a good quality mat placed at the entrance to the room will help by retaining dust and gravel. Clean up spillages of water and other liquids immediately, and be careful where you place flower and plant pots.

## COVERAGE

- 10 m<sup>2</sup> per litre per coat.

## STORAGE

- INTENSIV™ (Comp. A): store carefully, protect from frost (be especially careful when storing in vehicles).
- AQUA PRO HARDENER (Comp. B): not affected by frost.
- Seal both containers carefully after use. **IMPORTANT: wipe the neck of the Hardener to prevent the lid from sticking.**

## CLEANING AND MAINTENANCE

- INTENSIV™ gives you ease of maintenance for all parquets, wood floors and stairs.
- Remove dust regularly, using a vacuum cleaner or a dustpan and broom.
- Mop the surface occasionally using a damp mop, but never a soaking wet one. Stains can be removed with BLANCHON LAGOON®, BLANCHON CLEANER LISABRIL™ or a neutral detergent (follow manufacturer's recommendations for concentrations.)
- **IMPORTANT: allow 10 days to elapse before carrying out any cleaning or maintenance to give INTENSIV™ time to dry out thoroughly.**
- Do not use: floor cleaning machine, mop, silicone-based polishes, ammonia products or abrasive detergents, etc., i.e. all materials and products likely to damage the slip resistance of the product or increase its shine level.
- Heavy traffic areas finished with INTENSIV™ can be maintained on a regular basis with BLANCHON PROTECTORS Satin and CLEANER LISABRIL™ (see the relevant Technical Sheets). Frequency of maintenance will depend on usage and traffic.
- On INTENSIV™, only LAGOON® and CLEANER LISABRIL™ are recommended.

## REFINISHING

- Any refinishing of a previously sealed floor using INTENSIV™ should not be carried out before the wood has been sanded back to bare wood (see SURFACE PREPARATION and APPENDIX).

## TECHNICAL DATA

USE	Lacquer for parquet, wood flooring and stairs
RESIN TYPE	Comp. A: water-based polyurethanes - Comp. B: water-borne polyurethanes
AFNOR CLASSIFICATION	Family 1, class 6a2
DENSITY	1.03 [at 20°C, as per NF T 30020]
VISCOSITY	BROOKFIELD (Spindle 2, Speed 100 rpm at 20°C) Comp. A: 170 to 220 centipoises depending on finish - Comp. B: 400 centipoises
REGULATORY INFORMATION	Refer to the relevant Safety Data Sheets (available on <a href="http://www.blanchon.com">www.blanchon.com</a> or on <a href="http://www.quickfds.com">www.quickfds.com</a> ).
MIXING	9 parts INTENSIV™ Comp. A + 1 part INTENSIV™ Comp. B
RESANDABLE - RECOATABLE	4 hours, depending on temperature and moisture content
SAFETY INSTRUCTIONS	Do not apply below 12°C. Keep out of reach of children
RESISTANCE TO TABER ABRASION	Weight loss: 20 mg [CS 10 wheels, 1000 rpm, 1 kg]
RESISTANCE TO SHOCK	50 cm [400 g chuck] [as per NF T 30039]
RESISTANCE TO SCRATCHING	7H pencil
RESISTANCE TO HOUSEHOLD PRODUCTS	Vegetable oil, 40° alcohol, water, coffee, tea, ink: no adverse effects after 3 hours' exposure [after 10 days' drying, as per NF T 30053]. Do not use ammonia-based products

### APPENDIX: SANDING A WOOD FLOOR USING A MACHINE

- This is done using a special floor sander, with an edge sander for the edges and a scraper for the corners.
- The floor sander should be used in the direction of the light, or better still, in the direction of the wood grain.
- Work in even, regular "sweeps" to ensure that the entire surface is done in an identical manner.
- 1<sup>st</sup> pass: coarse grit (24, 30 or 36) to expose the bare wood and level it.
- 2<sup>nd</sup> pass: medium grit (50 or 60) to get a smooth, even surface.
- 3<sup>rd</sup> pass: fine grit (100 or 120) to obtain a good finish.
- Do all the edges of the room with the edge sander and scraper.
- Polishing with a buffing machine fitted with an abrasive mesh (80 or 120) ensures that the surface is perfectly prepared, especially in the case of flooring that has alternating lines (mosaics, chevrons, herringbone pattern, basket weave pattern, etc.).
- Remove all dust carefully, using a powerful vacuum cleaner, from the area to be lacquered, including any skirting boards, window ledges and radiators.

Technical Data Sheet approved by the Technical Service and issued in July 2018. Designed, developed and manufactured in France.  
The information contained in this Technical Data Sheet is provided in good faith as a guideline only.  
Under no circumstances can this information be considered as a guarantee given by us or incur our liability when our products are used.  
This Technical Data Sheet cancels and replaces all previous versions.

50 8<sup>ème</sup> Rue  
69800 SAINT-PRIEST - FRANCE  
Tél. 04 72 89 06 00 - Fax 04 78 70 07 18  
Export Lines: Tel: [0033] 472 89 06 09  
Fax: [0033] 472 89 06 02

**Blanchon**

BLANCHON - Est. 1832 - A stock company with a board of directors and a supervisory board, with a registered capital of 4 258 258  
390 112 886 RCS LYON - APE 2030 Z - E-mail: [info.uk@blanchon.com](mailto:info.uk@blanchon.com) - Internet : [www.blanchon.com](http://www.blanchon.com)